



Soft PVC hose with polyester yarn reinforcement, for the passage of cooling fluids, chemical solutions, food and compressed air.



SMOOTH SURFACES



FLEXIBILITY



ABRASION RESISTANCE



TEMPERATURE RANGE

-5°C +60°C
23°F +140°F



CHEMICAL RESISTANCE

PVC table



CRUSHING RESISTANCE



FOR FOOD

Suitable according to Reg. CE 1935/2004 and Reg. UE 10/2011 for contact with foodstuff that requires a simulating liquid type A B C, migration tests performed at 40°C for 24 hours.

Ø I.D.	Ø I.D.	Ø O.D.	TOTAL THICKNESS	WEIGHT	BENDING RADIUS	WORKING PRESSURE 1:3 23°C	WORKING PRESSURE 40°C	WORKING PRESSURE 60°C	BURSTING PRESSURE 23°C	COIL LENGTH	AVAILABILITY
inch	mm	mm	mm	g/m	mm	bar	bar	bar	bar	m	
	4	10	3	80	12	20	16	12	60	100	IN STOCK
3/16	5	11	3	90	15	20	16	12	60	100	IN STOCK
1/4	6	11	2.5	80	19	20	16	12	60	100	IN STOCK
1/4	6	12	3	105	17	20	16	12	60	100	IN STOCK
1/4	6	14	4	145	15	20	16	12	60	100	IN STOCK
	7	13	3	115	20	20	16	12	60	100	IN STOCK
5/16	8	13	2.5	105	28	18	13	9	54	100	IN STOCK
5/16	8	14	3	125	25	18	13	9	54	100	IN STOCK
5/16	8	17	4.5	220	22	18	13	9	54	100	IN STOCK
	9	15	3	135	32	18	13	9	54	100	IN STOCK
3/8	10	15	2.5	120	36	18	13	9	54	100	IN STOCK
3/8	10	16	3	150	30	18	13	9	54	100	IN STOCK
	12	17	2.5	130	35	12	9	6	36	50	IN STOCK
	12	18	3	180	35	12	9	6	36	50	IN STOCK
1/2	13	18	2.5	150	43	12	9	6	36	50	IN STOCK
1/2	13	19	3	175	52	12	9	6	36	50	IN STOCK
	15	21	3	215	60	10	7	4	30	50	IN STOCK
	15	23	4	280	60	10	7	4	30	50	IN STOCK
5/8	16	21	2.5	185	62	10	7	4	30	50	IN STOCK
5/8	16	22	3	210	60	10	7	4	30	50	IN STOCK
3/4	19	25	3	260	70	10	7	4	30	50	IN STOCK
3/4	19	26	3.5	300	70	10	7	4	30	50	IN STOCK
	22	30	4	420	85	8	5	3	24	50	IN STOCK
1	25	32	3.5	390	150	8	5	3	24	50	IN STOCK
1	25	33	4	450	110	8	5	3	24	50	IN STOCK
	30	38	4	560	170	8	5	3	24	50	IN STOCK
1 1/4	32	42	5	660	200	8	4	2	24	50	IN STOCK
	35	45	5	750	250	8	4	2	24	50	IN STOCK
1 1/2	38	48	5	870	300	8	4	2	24	50	IN STOCK
	40	50	5	880	350	8	4	2	24	50	IN STOCK
1 3/4	45	55	5	1000	420	8	4	2	24	50	IN STOCK
2	50	60	5	1100	500	8	4	2	24	25	ON DEMAND
2	50	62	6	1350	450	8	4	2	24	25	IN STOCK

All technical specifications apply to a temperature of 23°C ± 2°C (ISO 291). - Tolerance on all specifications ± 5%.